



Jacobson van den Berg (Hong Kong) Ltd.

8/F., Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408



尼龍-6 — 50%玻璃珠級
PA-6 — 50% GLASS BEADS GRADE
NYLON GRILON BK-50

性能 Properties	測驗方法 Test Method	測試條件 Conditions		單位 Units	GRILON BK-50
物理性能 Physical Properties					
填充成份 Filler Content	-	-		%	50
比重 Density	ISO 1183	dry 乾燥時		g/cm ³	1.55
吸水率 Water Absorption	ISO 62	23°C/sat.		%	5
濕水率 Moisture Absorption	ISO 62	23°C/50% r.h.		%	1.5
成形收縮率 Linear Molding Shrinkage	ISO 294 / EMS	long. / trans.	dry 乾燥時	%	0.7 / 0.75
熱性能 Thermal Properties					
融點 Melting Point	ISO 11357	DSC	dry 乾燥時	°C	222
熱變形溫度 Heat Deflection Temperature	ISO 75	HDT/A (1.80 MPa)	dry 乾燥時	°C	95
		HDT/C (8.00 MPa)			45
熱膨脹系數 Thermal Expansion Coefficient	ISO 11359	23-80°C long. / trans.	dry 乾燥時	10 ⁻⁴ / K	0.7 / 0.7
最高使用溫度 Maximal Usage Temperature	EMS	long term / short term	dry 乾燥時	°C	80-110 / 160
燃燒性 Flammability	UL 94	-		rating	HB (0.89mm)
機械性能 Mechanical Properties					
拉伸強度 Tensile Strength	ISO 527	yield / break 50 mm/min	dry 乾燥時	MPa	95 / 85
			cond. 吸濕後		45 / 40
拉伸長度 Tensile Elongation	ISO 527	yield / break 50 mm/min	dry 乾燥時	%	4 / 8
			cond. 吸濕後		8 / 25
拉伸模量 Tensile E-Modulus	ISO 527	1 mm/min	dry 乾燥時	MPa	6,100
			cond. 吸濕後		1,700
Charpy 衝擊強度 Charpy Impact Strength	ISO 179/1eU	23°C / -30°C	dry 乾燥時	kJ/m ²	60 / 35
	ISO 179/1eA	23°C / -30°C (notched)	dry 乾燥時 cond. 吸濕後		4 / 3
硬度 Hardness	ISO 2039-1	dry 乾燥時		MPa	225
		cond. 吸濕後			90
電性能 Electrical Properties					
耐電壓 Dielectric Strength	IEC 243-1	K20 / P50	dry 乾燥時	kV/mm	36
			cond. 吸濕後		29
比較痕跡指數 Comparative Tracking Index	IEC 112	CTI	dry 乾燥時	-	500
			cond. 吸濕後		450
表面電阻系數 Specific Surface Resistivity	IEC 93	dry 乾燥時		Ω.cm	10 ¹¹
		cond. 吸濕後			10 ¹⁰
體積電阻系數 Volume Resistivity	IEC 93	dry 乾燥時		Ω	10 ¹³
		cond. 吸濕後			10 ¹¹

上列數據任僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.